Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2011-2013 LIC. NO.
9669.143

Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2014-2016 LIC. NO.

LICENSED
HAWAII
DEPT. OF AGRICULTURE
Period 1999-2001 No. 9669.143

2002-2004
2005-2007

PRECAUTIONARY STATEMENTS
DANGER
KEEP OUT OF REACH OF CHILDREN

HAZARD TO HUMANS AND DOMESTIC ANIMALS: Danger. Corrosive. Causes eye damage and skin irritation. Harmful if absorbed through skin. Do not get in eyes or on clothing. Avoid contact with skin. Wear goggles or face shield and rubber gloves when handling. Avoid contamination of food. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash before reuse.

STATEMENT OF PRACTICAL TREATMENT:

In case of contact, immediately flush eyes and skin with plenty of water for at least 15 minutes. For eyes call a physician. If swallowed, drink promptly large quantities of water. Avoid alcohol. Call physician immediately. Note to physician: Probable mucosal damage may contraindicate the use of gastric lavage.

ENVIRONMENTAL HAZARD

This pesticide is toxic to fish and aquatic invertebrates. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other public waters unless this product is specifically identified and addressed in an NPDES permit. Do not discharge effluent to sewer systems without previously notifying the sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARDS

Flammable. Keep away from heat and open flame.

STORAGE AND DISPOSAL

Do not contaminate water, food, feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are toxic. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to label instructions contact your State Pesticide or Environmental Control Agency or the Hazardous Waste representative of the nearest EPA Regional office for guidance.

CONTAINER DISPOSAL: Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in an approved landfill, or by other approved state and local alternative procedures.

RECEIVED
FEB 22 1999
Pesticides Branch

Product Identity

Interspeed® 340 NA Polishing Antifouling

Order Number

BQA357 RED

FOR COMMERCIAL USE ONLY

Active Ingredient:	
CUPROUS OXIDE	38.63%
4,5-Dichloro-2-n-octyl-3(2H)-isothiazolone	3.00%
Inert Ingredients:	58.37%
	100.00%

COPPER AS METALLIC = 34.94%

KEEP OUT OF REACH OF CHILDREN

DANGER

- See side panel for additional Precautionary Statement -

EPA Reg. No.: 2693-180 EPA Est. No.: 2693-NJ-1

NET CONTENTS:
FIVE U.S. GALLONS (18.927 LITERS)

Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2008-2010 LIC. NO.

INTERSPEED® 340 NA RED ANTIFOULING

DIRECTIONS FOR USE:
It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: This product is designed to control a wide range of fouling organisms over extended service periods. The product is formulated with an innovative dual biocide copolymer system. Extended protection is possible since performance is directly proportional to the amount of product applied. This product releases biocide by the constant exposure of new paint to the water. Because of this, vessels used regularly experience optimal performance.*

SURFACE PREPARATION AND COMPATIBILITY: Surface preparation directions must be followed exactly in order to insure adhesion. Surface must always be clean and dry prior to painting. This product can be applied over most TBT copolymer and traditional long life antifouling paints as long as the old coating has been aged and is tightly adhered and in sound condition. This product should not be applied over Teflon or graphite type paints.

GENERAL APPLICATION PROCEDURES: Airless spray is recommended: Tip Size 21-26 thou., pump ratio of 30:1 or greater. For small areas, brush or roller application may be used but multiple coats may be required to achieve the required dry film thickness. It is recommended to apply by airless spray two (2) or three (3) full coats of this product.

MIXING AND THINNING INSTRUCTIONS: Mix thoroughly with power mixer prior to application. This coating is designed to be applied without thinning. Should thinning be necessary consult your International representative prior to altering this coating.

CLEAN UP: For tools, equipment, etc., use INTERNATIONAL GTA007.

MINIMUM DRY AND LAUNCHING TIMES: Minimum drying time between coats is 12 hours, and before launching is 24 hours at a temperature of 73°F.

THEORETICAL COVERAGE: 331 square feet per gallon, per coat at 3.0 mils D.F.T. Consult your International representative for practical application coverages. Practical square foot coverage per gallon, per coat is directly proportional to surface, application techniques and climatic conditions.

APPLICATION SYSTEMS

EXISTING COPOLYMER ANTIFOULING SYSTEMS - GOOD HULL CONDITION: High pressure fresh water wash with a minimum of 250 p.s.i. to remove all marine growth, slime, salts, etc. Spot blast all areas of corrosion to Near White Metal. Blow down with clean and dry high pressure air to remove all spent abrasives. Apply an approved underwater anticorrosive system.

POOR HULL CONDITIONS: For "optimum" results, blast entire area to Near White Metal. Apply an approved underwater anticorrosive system.

NEW SHIP CONSTRUCTION: Blast entire area to Near White Metal. Blow down with clean and dry high pressure air to remove all spent abrasives. Apply an approved underwater anticorrosive system.

*This product is only for use on steel boat/ship hulls operating in salt water. Not suitable for use on aluminum boat hulls.

DISCLAIMER: The performance of any marine coating depends on many factors outside the control of Courtaulds Coatings Inc. including the surface preparation, proper application, and the environmental conditions. Therefore, Courtaulds Coatings Inc. cannot guarantee the suitability of this product for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND MERCHANTABILITY ARE EXCLUDED. COURTAULDS COATINGS INC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at Courtaulds Coatings Inc's option.

Rev. 11/98

COURTAULDS COATINGS

Courtaulds Coatings, Inc.
2270 Morris Ave, Union, NJ 07083