LICENSED
HAWAII
DEPT. OF AGRICULTURE
Rev. Period 2006-2008 No. 9669.151

Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2009-2011 LIC. NO.

Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2012-2014 LIC. NO.

Department of Agriculture
STATE OF HAWAII
LICENSED
PERIOD 2015-2017 LIC. NO.
9669.151

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN
WARNING
See Side Panel for Additional Precautionary Statements

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1
EPA REG NO. 2693-132

ONE U.S. GALLON
(3.785 L)

5584
SHARK WHITE

RECEIVED
SEP 27 2005
Pesticides Branch

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice.

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

X, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

X.Interlux.
International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1

EPA REG NO. 2693-132

ONE U.S. GALLON
(3.785 L)

5583
BLACK

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice.

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate -- vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

®, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

ONE U.S. GALLON
(3.785 L)

5585
BROWN

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1

EPA REG NO. 2693-132

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours
77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray, do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

®, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

5586
DARK BLUE
(SEA RAY)

ONE U.S. GALLON
(3.785 L)

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1

EPA REG NO. 2693-132

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice.

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

®, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

5582
RED

ONE U.S. GALLON
(3.785 L)

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1

EPA REG NO. 2693-132

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or pucture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

®, Interlux and Micron CSC are registered trademarks of Akzo Nobel

Interlux.
International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

5581
GREEN

ONE U.S. GALLON
(3.785 L)

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1

EPA REG NO. 2693-132

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

®, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

Interlux.
International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

Interlux®

MicronCSC®

Antifouling Performance for All Conditions
Multi-Season, Self-Polishing, No Buildup
Haul & Relaunch Without Repainting

KEEP OUT OF REACH OF CHILDREN

WARNING

See Side Panel for Additional Precautionary Statements

5580
BLUE

ONE U.S. GALLON
(3.785 L)

ACTIVE INGREDIENT	PERCENT
CUPROUS OXIDE	37.20%
INERT INGREDIENTS	62.80%
	100.00%

COPPER AS METALLIC 32.90%

CONTAINS PETROLEUM DISTILLATES

EPA EST 2693-NJ-1
EPA REG NO. 2693-132

MICRON CSC®

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

PRODUCT DESCRIPTION: MICRON CSC® is the newest in a series of multi-season antifouling paints based on Controlled Solubility Copolymer™ technology. These products are designed to wear away (polish) at a controlled rate similar to a bar of soap. As a result there will be a reduced buildup of old coatings and minimized sanding at reapplication. In addition, this technology allows the boat to be hauled and relaunched the following season without repainting. **MICRON CSC®** contains high solids and dries to bright colors. It will provide excellent antifouling longevity against all types of algae, weeds, barnacles, and other shell fouling. **MICRON CSC®** can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

COMPATIBILITY: MICRON CSC® can be applied over most hard conventional antifouling paints as long as the old coating is tightly adhered and is in sound condition. **MICRON CSC®** should not be applied over MICRON® 33, MICRON® 44 or soft antifouling paints. These old coatings should be removed. **MICRON CSC®** is compatible with conventional bottom paints after they have been thoroughly sanded with 80 grit wet or dry sandpaper.

VOC: Less than 400 grams/liter (3.34 lbs./gallon) as supplied

THINNER: Brushing - Brush-Ease 433™
Spraying - Special Thinner 216™

THINNING: Thin only when necessary. Do not exceed 10% by volume.

CLEAN-UP: Special Thinner 216™ or Brush-Ease 433™.

THEORETICAL COVERAGE: 440 square feet per gallon/coat will yield 2 mils dry film thickness.

DRY TIMES: Touch dry - 2 hours

77°F (25°C) Dry to overcoat - 16 hours minimum*
Dry to launch - 16 hours minimum*

APPLICATION TEMPERATURE: 50°F (10°C) and above. (Air and hull).

* If either the air or hull temperature falls below 50°F (10°C) during the 16 hour dry time extend the dry times to a minimum of 36 hours.

APPLICATION SYSTEMS

GENERAL APPLICATION PROCEDURES: Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of **MICRON CSC®** by brush or solvent resistent 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Interlux® Brush-Ease 433™ to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to insure that **MICRON CSC®** does not wash away before the other areas of the bottom.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Interlux® Special Thinner 216™. Apply at least 2 coats of **MICRON CSC®**, allowing proper dry times.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with Interlux® Interstrip® 299E for fiberglass, Interlux® Interstrip® 299E for wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

BARE FIBERGLASS - NO SAND SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202™ changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Apply one thin, continuous coat of Interlux® Fiberglass No Sand Primer YPA200 with brush or roller. Do not spray; do not sand. Allow to cure 2 hours but no more than 3 hours. Apply first coat of **MICRON CSC®** and allow to dry overnight. Apply at least one more coat of **MICRON CSC®** allowing proper dry times.

BARE FIBERGLASS - SANDING SYSTEM: Wash entire surface thoroughly with Interlux® Fiberglass Solvent Wash 202, changing rags frequently. Before liquid dries, wipe clean with a dry cloth. (Be sure all wax and other contaminants are removed). Failure to properly clean the surface will result in paint delamination. Sand any imperfections and repair with Interlux® Watertite YAV135; sand and wipe clean. Sand entire gelcoat well with 80 grit wet or dry sandpaper until a flat, matte finish is obtained; wipe surface clean with Interlux® Fiberglass Solvent Wash 202™. Apply 2 or more coats of **MICRON CSC®** allowing proper dry times.

BARE WOOD: Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Interlux® Brush-Ease 433™. Repair imperfections with Interlux® Watertite YAV135; sand and wipe clean. Apply first coat of **MICRON CSC®** reduced with Interlux® Brush-Ease 433™ (10% maximum). Fill seams with Interlux® Seam Compound 30 between first and second coats of **MICRON CSC®**.

UNDERWATER METALS: Contact the Interlux® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: MICRON CSC® SHARK WHITE 5584 may change color at the waterline.

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapor or spray mist. While spraying paint or sanding or sand blasting boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID

If Swallowed:
- Immediately call a poison control center or doctor.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give **any** liquid to the person.
- Do not give anything by mouth to an unconscious person.

If on skin or clothing:
- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes
- Call a poison control center or doctor for treatment advice.

If inhaled:
- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

If in eyes:
- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

Other: Have the product container or label with you when calling a poison control center or doctor or going for treatment.

Note to Physician: Contains petroleum distillate – vomiting may cause aspiration pneumonia.

ENVIRONMENTAL HAZARD: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans or other waters unless in accordance with the requirements of a National Pollutant Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent containing this product to sewer systems without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

PHYSICAL OR CHEMICAL HAZARD: Flammable. Keep away from heat and open flame.

STORAGE & DISPOSAL: Do not contaminate water, food, feed by storage or disposal.

PESTICIDE DISPOSAL: Pesticide, spray mixture or rinsate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

CONTAINER DISPOSAL: Triple rinse (or equivalent) then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

FOR CHEMICAL EMERGENCY, SPILL, LEAK, EXPOSURE OR ACCIDENT, CALL TOLL FREE: CHEMTREC **1-800-424-9300** (DAY OR NIGHT) MEDICAL ADVISORY: CONTACT YOUR LOCAL POISON CONTROL CENTER OR CALL **1-800-854-6813.**

Rev. 4/03

✕, Interlux and Micron CSC are registered trademarks of Akzo Nobel.

✕.Interlux.
International Paint LLC
2270 Morris Ave., Union, NJ 07083 • 908-686-1300

0 81948 15580 9

AKZO NOBEL

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT, UNDER ANY CIRCUMSTANCES, BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.