

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

AkzoNobel



AQUA-ONE™

PRODUCT DESCRIPTION: Aqua-One is a water-based antifouling delivering solid protection from barnacles, zebra mussels, slime, algae and other forms of marine fouling. The abrasive action wears away with use, minimizing build-up and heavy sanding associated with the build-up of old spent coatings. It is for use below the waterline in all waters (salt, brackish and fresh water). Apply Aqua-One on power and sail boats; fiberglass, wood, and properly primed metal boat hulls. **Do not use on aluminum.**

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.
COMPATIBILITY: Aqua-One can be applied over most antifouling paints as long as the old coating is tightly adhered and is in sound condition. When applying over conventional antifouling paints, thoroughly sand with 80 grit wet-or-dry sandpaper. If applying over self-polishing type copolymer antifouling, heavy sanding is required. Soft rosin based coatings should be removed prior to application of Aqua-One.

V.O.C.: Less than 150 grams/liter
COATS REQUIRED: 2 coats. 3 coats on bare wood
THINNER: Water
THINNING: Thin only if necessary. Do not exceed 10% by volume
CLEAN UP: Soap and water. Be sure to observe proper disposal procedures for all antifouling paints.
THEORETICAL COVERAGE: 375 sq. ft./gal/coat.
APPLICATION TEMPERATURE: 45°F (7°C) and above.

APPLICATION SYSTEMS:

Stir thoroughly (do not shake) Apply at least two full coats (three on bare wood) of Aqua-One by synthetic brush or 3/8" nap roller. Do not apply thin coats. If during application, the brush or roller drags, thin with clean tap water to improve handling. During the drying and curing process there may appear to be color changes resulting in an uneven appearance. This discoloration will disappear as the finish dries to a deep uniform color.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit sandpaper; wipe surface clean with tap water. Apply at least two coats of Aqua-One, allowing proper dry times. See compatibility section for additional information.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with INTERSTRIP 299e and proceed with application system for bare work as described below.

BARE FIBERGLASS (Polyester or Vinylester) - It is very important that bare fiberglass be properly prepared to remove the mold release wax completely to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following Interlux products. **Fiberglass Surface Prep YMA601V** or **Fiberglass Solvent Wash 202** following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface. If the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

BARE FIBERGLASS - NO SAND SYSTEM: After the surface has been prepared as described above - Apply one continuous coat of **Fiberglass No Sand Primer YPA200** or **InterProtect 2000E** with brush or roller. Follow label directions for overcoating. Apply at least two coats of Aqua-One following dry times below.

BARE FIBERGLASS - SANDING SYSTEM: After the surface has been prepared as described above - Sand entire surface well with 80 grit sandpaper until a flat, matte finish is obtained; wipe off sanding residue with **FIBERGLASS SOLVENT WASH 202™**. Apply two coats of Aqua-One following dry times below.

BARE WOOD: Sand entire surface with 80 grit sandpaper. Wipe off sanding residue. Repair any imperfections with **WATERTITE EPOXY FILLER**; sand and wipe clean. Apply first coat of Aqua-One reduced with tap water (10% maximum). Apply two additional coats unreduced following proper dry times between coats. Fill seams (if necessary) with **SEAM COMPOUND 30** between first and second coats of antifouling paint.

UNDERWATER METALS: Contact the INTERLUX® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: Keep from freezing.

Temp °C	Overcoating Time		Launch Time		
			Dry 50% Relative Humidity	75% Relative Humidity	Humid 85% Relative Humidity
	Min	Max	Min	Min	Min
45°F (5°C)	16 Hrs	30 days	48 Hours	72 Hours	Do Not Apply
50°F (10°C)	8 Hrs	30 days	36 Hours	48 Hours	Do Not Apply
60°F (15°C)	4 Hrs	30 days	16 Hours	24 Hours	48 Hours
75°F (24°C)	2 Hrs	30 days	5 Hours	7 Hours	36 Hours
95°F (35°C)	1 Hr	30 days	2 Hours	5 Hours	24 Hours

Color difference may occur between actual paint and color swatch on front of can.

Aqua-One™

Performance Ablative

Water-Based Ablative Antifouling Easy Application and Clean-Up Compatible Over Most Antifouling Paints

**KEEP OUT OF REACH OF CHILDREN
WARNING**

See Side Panel for Additional Precautionary Statements

**YBE179
BLACK**

**ONE U.S. GALLON
(3.785 L)**

ACTIVE INGREDIENT: CUPROUS OXIDE 28.45%
 CAS# 1317-39-1
INERT INGREDIENTS 71.55%
 100.00%
 COPPER AS METALLIC 25.74%
 EPA EST 2693-TX-1
 EPA REG NO. 2693-193

yachtpaint.com

**PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS
WARNING**

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe vapor. While sanding boat surface, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID:

IF SWALLOWED:

- Call a poison control center or doctor immediately for treatment advice.
- Have person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

IF ON SKIN OR CLOTHING:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

IF INHALED:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

IF IN EYES:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

OTHER: Have the product container or label with you when calling a poison control center or doctor, or going for treatment.

ENVIRONMENTAL HAZARDS:

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.
PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by uses according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Non-refillable container. Do not re-use or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container 1/4 full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

For Chemical Emergency, Spill, Leak, Exposure or Accident, Call TollFree - Day or Night - **Chemtrec 1-800-424-9300**.
 Medical Advisory Number - Contact your Local Poison Control Center or call **1-800-854-6813**.

YBE179/1

Interlux® are registered trademarks of Akzo Nobel.

Interlux.
 International Paint LLC.
 6001 Antoine Dr. Houston, TX USA 77091 • 713-682-1711



0 81948 00228 8

MADE IN THE U.S.A

ZU03989a

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

AkzoNobel



Aqua-One™

Performance Ablative

Water-Based Ablative Antifouling
Easy Application and Clean-Up
Compatible Over Most Antifouling Paints

**KEEP OUT OF REACH OF CHILDREN
WARNING**

See Side Panel for Additional Precautionary Statements

**ONE U.S. GALLON
(3.785 L)**

**YBE169
BLUE**

ACTIVE INGREDIENT:	PERCENT
CUPROUS OXIDE	28.45%
CAS# 1317-39-1	
INERT INGREDIENTS	<u>71.55%</u>
	100.00%
COPPER AS METALLIC	25.74%
EPA EST 2693-TX-1	
EPA REG NO. 2693-193	

AQUA-ONE™

PRODUCT DESCRIPTION: Aqua-One is a water-based antifouling delivering solid protection from barnacles, zebra mussels, slime, algae and other forms of marine fouling. The abrasive action wears away with use, minimizing build-up and heavy sanding associated with the build-up of old spent coatings. It is for use below the waterline in all waters (salt, brackish and fresh water). Apply Aqua-One on power and sail boats; fiberglass, wood, and properly primed metal boat hulls. **Do not use on aluminum.**

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

COMPATIBILITY: Aqua-One can be applied over most antifouling paints as long as the old coating is tightly adhered and is in sound condition. When applying over conventional antifouling paints, thoroughly sand with 80 grit wet-or-dry sandpaper. If applying over self-polishing type copolymer antifouling, heavy sanding is required. Soft rosin based coatings should be removed prior to application of Aqua-One.

V.O.C.: Less than 150 grams/liter

COATS REQUIRED: 2 coats. 3 coats on bare wood

THINNER: Water

THINNING: Thin only if necessary. Do not exceed 10% by volume

CLEAN UP: Soap and water. Be sure to observe proper disposal procedures for all antifouling paints.

THEORETICAL COVERAGE: 375 sq. ft./gal/coat.

APPLICATION TEMPERATURE: 45°F (7°C) and above.

APPLICATION SYSTEMS:

Stir thoroughly (do not shake) Apply at least two full coats (three on bare wood) of Aqua-One by synthetic brush or 3/8" nap roller. Do not apply thin coats. If during application, the brush or roller drags, thin with clean tap water to improve handling. During the drying and curing process there may appear to be color changes resulting in an uneven appearance. This discoloration will disappear as the finish dries to a deep uniform color.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit sandpaper; wipe surface clean with tap water. Apply at least two coats of Aqua-One, allowing proper dry times. See compatibility section for additional information.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with INTERSTRIP 299e and proceed with application system for bare work as described below.

BARE FIBERGLASS (Polyester or Vinylester) - It is very important that bare fiberglass be properly prepared to remove the mold release wax completely to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following Interlux products. **Fiberglass Surface Prep YMA601V** or **Fiberglass Solvent Wash 202** following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface. If the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

BARE FIBERGLASS - NO SAND SYSTEM: After the surface has been prepared as described above - Apply one continuous coat of **Fiberglass No Sand Primer YPA200** or **InterProtect 2000E** with brush or roller. Follow label directions for overcoating. Apply at least two coats of Aqua-One following dry times below.

BARE FIBERGLASS - SANDING SYSTEM: After the surface has been prepared as described above - Sand entire surface well with 80 grit sandpaper until a flat, matte finish is obtained; wipe off sanding residue with **FIBERGLASS SOLVENT WASH 202™**. Apply two coats of Aqua-One following dry times below.

BARE WOOD: Sand entire surface with 80 grit sandpaper. Wipe off sanding residue. Repair any imperfections with **WATERTITE EPOXY FILLER**; sand and wipe clean. Apply first coat of Aqua-One reduced with tap water (10% maximum). Apply two additional coats unreduced following proper dry times between coats. Fill seams (if necessary) with **SEAM COMPOUND 30** between first and second coats of antifouling paint.

UNDERWATER METALS: Contact the INTERLUX® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: Keep from freezing.

Temp °C	Overcoating Time		Launch Time		
			Dry 50% Relative Humidity	75% Relative Humidity	Humid 85% Relative Humidity
	Min	Max	Min	Min	Min
45°F (5°C)	16 Hrs	30 days	48 Hours	72 Hours	Do Not Apply
50°F (10°C)	8 Hrs	30 days	36 Hours	48 Hours	Do Not Apply
60°F (15°C)	4 Hrs	30 days	16 Hours	24 Hours	48 Hours
75°F (24°C)	2 Hrs	30 days	5 Hours	7 Hours	36 Hours
95°F (35°C)	1 Hr	30 days	2 Hours	5 Hours	24 Hours

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe vapor. While sanding boat surface, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID:

IF SWALLOWED:

- Call a poison control center or doctor immediately for treatment advice.
- Have person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

IF ON SKIN OR CLOTHING:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

IF INHALED:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

IF IN EYES:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

OTHER: Have the product container or label with you when calling a poison control center or doctor, or going for treatment.

ENVIRONMENTAL HAZARDS:

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by uses according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Non-refillable container. Do not re-use or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container 1/4 full with water and recap. Shake for 10 seconds. Pour rinsate into application equipment or a mix tank or store rinsate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

For Chemical Emergency, Spill, Leak, Exposure or Accident, Call TollFree - Day or Night - **Chemtrec 1-800-424-9300**.

Medical Advisory Number - Contact your Local Poison Control Center or call **1-800-854-6813**.

YBE169/1

Interlux® are registered trademarks of Akzo Nobel.

Interlux®

International Paint LLC.
6001 Antoine Dr. Houston, TX USA 77091 • 713-682-1711



0 81948 00225 7

MADE IN THE U.S.A

yachtpaint.com

ZU0395a

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

AkzoNobel



Aqua-One™

Performance Ablative

Water-Based Ablative Antifouling
Easy Application and Clean-Up
Compatible Over Most Antifouling Paints

**KEEP OUT OF REACH OF CHILDREN
WARNING**

See Side Panel for Additional Precautionary Statements

**ONE U.S. GALLON
(3.785 L)**

**YBE159
GREEN**

ACTIVE INGREDIENT:	PERCENT
CUPROUS OXIDE	28.45%
CAS# 1317-39-1	
INERT INGREDIENTS	<u>71.55%</u>
	100.00%
COPPER AS METALLIC	25.74%
EPA EST 2693-TX-1	
EPA REG NO. 2693-193	

AQUA-ONE™

PRODUCT DESCRIPTION: Aqua-One is a water-based antifouling delivering solid protection from barnacles, zebra mussels, slime, algae and other forms of marine fouling. The ablativ action wears away with use, minimizing build-up and heavy sanding associated with the build-up of old spent coatings. It is for use below the waterline in all waters (salt, brackish and fresh water). Apply Aqua-One on power and sail boats; fiberglass, wood, and properly primed metal boat hulls. **Do not use on aluminum.**

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.
COMPATIBILITY: Aqua-One can be applied over most antifouling paints as long as the old coating is tightly adhered and is in sound condition. When applying over conventional antifouling paints, thoroughly sand with 80 grit wet-or-dry sandpaper. If applying over self-polishing type copolymer antifouling, heavy sanding is required. Soft rosin based coatings should be removed prior to application of Aqua-One.
V.O.C.: Less than 150 grams/liter
COATS REQUIRED: 2 coats. 3 coats on bare wood
THINNER: Water
THINNING: Thin only if necessary. Do not exceed 10% by volume
CLEAN UP: Soap and water. Be sure to observe proper disposal procedures for all antifouling paints.
THEORETICAL COVERAGE: 375 sq. ft./gal/coat.
APPLICATION TEMPERATURE: 45°F (7°C) and above.

APPLICATION SYSTEMS:

Stir thoroughly (do not shake) Apply at least two full coats (three on bare wood) of Aqua-One by synthetic brush or 3/8" nap roller. Do not apply thin coats. If during application, the brush or roller drags, thin with clean tap water to improve handling. During the drying and curing process there may appear to be color changes resulting in an uneven appearance. This discoloration will disappear as the finish dries to a deep uniform color.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit sandpaper; wipe surface clean with tap water. Apply at least two coats of Aqua-One, allowing proper dry times. See compatibility section for additional information.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with INTERSTRIP 299e and proceed with application system for bare work as described below.

BARE FIBERGLASS (Polyester or Vinylester) - It is very important that bare fiberglass be properly prepared to remove the mold release wax completely to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following Interlux products. **Fiberglass Surface Prep YMA601V** or **Fiberglass Solvent Wash 202** following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface. If the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

BARE FIBERGLASS - NO SAND SYSTEM: After the surface has been prepared as described above - Apply one continuous coat of **Fiberglass No Sand Primer YPA200** or **InterProtect 2000E** with brush or roller. Follow label directions for overcoating. Apply at least two coats of Aqua-One following dry times below.

BARE FIBERGLASS - SANDING SYSTEM: After the surface has been prepared as described above - Sand entire surface well with 80 grit sandpaper until a flat, matte finish is obtained; wipe off sanding residue with **FIBERGLASS SOLVENT WASH 202™**. Apply two coats of Aqua-One following dry times below.

BARE WOOD: Sand entire surface with 80 grit sandpaper. Wipe off sanding residue. Repair any imperfections with **WATERTITE EPOXY FILLER**; sand and wipe clean. Apply first coat of Aqua-One reduced with tap water (10% maximum). Apply two additional coats unreduced following proper dry times between coats. Fill seams (if necessary) with **SEAM COMPOUND 30** between first and second coats of antifouling paint.

UNDERWATER METALS: Contact the INTERLUX® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: Keep from freezing.

Temp °C	Overcoating Time		Launch Time		
			Dry 50% Relative Humidity	75% Relative Humidity	Humid 85% Relative Humidity
	Min	Max	Min	Min	Min
45°F (5°C)	16 Hrs	30 days	48 Hours	72 Hours	Do Not Apply
50°F (10°C)	8 Hrs	30 days	36 Hours	48 Hours	Do Not Apply
60°F (15°C)	4 Hrs	30 days	16 Hours	24 Hours	48 Hours
75°F (24°C)	2 Hrs	30 days	5 Hours	7 Hours	36 Hours
95°F (35°C)	1 Hr	30 days	2 Hours	5 Hours	24 Hours

Color difference may occur between actual paint and color swatch on front of can.

**PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS
WARNING**

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe vapor. While sanding boat surface, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID:

IF SWALLOWED:

- Call a poison control center or doctor immediately for treatment advice.
- Have person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

IF ON SKIN OR CLOTHING:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

IF INHALED:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

IF IN EYES:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

OTHER: Have the product container or label with you when calling a poison control center or doctor, or going for treatment.

ENVIRONMENTAL HAZARDS:

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinate is a violation of Federal Law. If these wastes cannot be disposed of by uses according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Non-refillable container. Do not re-use or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container 1/4 full with water and recap. Shake for 10 seconds. Pour rinate into application equipment or a mix tank or store rinate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

For Chemical Emergency, Spill, Leak, Exposure or Accident, Call TollFree - Day or Night - **Chemtrec 1-800-424-9300.**

Medical Advisory Number - Contact your Local Poison Control Center or call **1-800-854-6813.**

YBE159/1

Interlux® are registered trademarks of Akzo Nobel.

Interlux®

International Paint LLC.
6001 Antoine Dr. Houston, TX USA 77091 • 713-682-1711



0 81948 00223 3

MADE IN THE U.S.A

yachtpaint.com

ZU09393qa

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of International Paint LLC, including surface preparation, proper application, and environmental conditions. Therefore, International Paint LLC cannot guarantee this product's suitability for your particular purpose or application. IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY ARE EXCLUDED. INTERNATIONAL PAINT LLC SHALL NOT BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at International Paint LLC's option.

AkzoNobel



Aqua-One™

Performance Ablative

Water-Based Ablative Antifouling
Easy Application and Clean-Up
Compatible Over Most Antifouling Paints

**KEEP OUT OF REACH OF CHILDREN
WARNING**

See Side Panel for Additional Precautionary Statements

**ONE U.S. GALLON
(3.785 L)**

**YBE149
RED**

ACTIVE INGREDIENT:	PERCENT
CUPROUS OXIDE	28.45%
CAS# 1317-39-1	
INERT INGREDIENTS	<u>71.55%</u>
	100.00%
COPPER AS METALLIC	25.74%
EPA EST 2693-TX-1	
EPA REG NO. 2693-193	

AQUA-ONE™

PRODUCT DESCRIPTION: Aqua-One is a water-based antifouling delivering solid protection from barnacles, zebra mussels, slime, algae and other forms of marine fouling. The abrasive action wears away with use, minimizing build-up and heavy sanding associated with the build-up of old spent coatings. It is for use below the waterline in all waters (salt, brackish and fresh water). Apply Aqua-One on power and sail boats; fiberglass, wood, and properly primed metal boat hulls. **Do not use on aluminum.**

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

COMPATIBILITY: Aqua-One can be applied over most antifouling paints as long as the old coating is tightly adhered and is in sound condition. When applying over conventional antifouling paints, thoroughly sand with 80 grit wet-or-dry sandpaper. If applying over self-polishing type copolymer antifouling, heavy sanding is required. Soft rosin based coatings should be removed prior to application of Aqua-One.

V.O.C.: Less than 150 grams/liter

COATS REQUIRED: 2 coats. 3 coats on bare wood

THINNER: Water

THINNING: Thin only if necessary. Do not exceed 10% by volume

CLEAN UP: Soap and water. Be sure to observe proper disposal procedures for all antifouling paints.

THEORETICAL COVERAGE: 375 sq. ft./gal/coat.

APPLICATION TEMPERATURE: 45°F (7°C) and above.

APPLICATION SYSTEMS:

Stir thoroughly (do not shake) Apply at least two full coats (three on bare wood) of Aqua-One by synthetic brush or 3/8" nap roller. Do not apply thin coats. If during application, the brush or roller drags, thin with clean tap water to improve handling. During the drying and curing process there may appear to be color changes resulting in an uneven appearance. This discoloration will disappear as the finish dries to a deep uniform color.

PREVIOUSLY PAINTED SURFACES - GOOD CONDITION: Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit sandpaper; wipe surface clean with tap water. Apply at least two coats of Aqua-One, allowing proper dry times. See compatibility section for additional information.

PREVIOUSLY PAINTED SURFACES - POOR CONDITION: Completely remove all old antifouling paint with INTERSTRIP 299e and proceed with application system for bare work as described below.

BARE FIBERGLASS (Polyester or Vinylester) - It is very important that bare fiberglass be properly prepared to remove the mold release wax completely to prevent delamination of the antifouling paint. Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following Interlux products. **Fiberglass Surface Prep YMA601V** or **Fiberglass Solvent Wash 202** following the product label instructions. To be certain that all of the contamination has been removed, run water over the surface. If the water beads up or separates, clean again. When the water sheets off, all contamination has been removed. After the surface has been properly cleaned, proceed with one of the application systems below.

BARE FIBERGLASS - NO SAND SYSTEM: After the surface has been prepared as described above - Apply one continuous coat of **Fiberglass No Sand Primer YPA200** or **InterProtect 2000E** with brush or roller. Follow label directions for overcoating. Apply at least two coats of Aqua-One following dry times below.

BARE FIBERGLASS - SANDING SYSTEM: After the surface has been prepared as described above - Sand entire surface well with 80 grit sandpaper until a flat, matte finish is obtained; wipe off sanding residue with **FIBERGLASS SOLVENT WASH 202™**. Apply two coats of Aqua-One following dry times below.

BARE WOOD: Sand entire surface with 80 grit sandpaper. Wipe off sanding residue. Repair any imperfections with **WATERTITE EPOXY FILLER**; sand and wipe clean. Apply first coat of Aqua-One reduced with tap water (10% maximum). Apply two additional coats unreduced following proper dry times between coats. Fill seams (if necessary) with **SEAM COMPOUND 30** between first and second coats of antifouling paint.

UNDERWATER METALS: Contact the INTERLUX® Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

NOTE: Keep from freezing.

Temp °C	Overcoating Time		Launch Time		
			Dry 50% Relative Humidity	75% Relative Humidity	Humid 85% Relative Humidity
	Min	Max	Min	Min	Min
45°F (5°C)	16 Hrs	30 days	48 Hours	72 Hours	Do Not Apply
50°F (10°C)	8 Hrs	30 days	36 Hours	48 Hours	Do Not Apply
60°F (15°C)	4 Hrs	30 days	16 Hours	24 Hours	48 Hours
75°F (24°C)	2 Hrs	30 days	5 Hours	7 Hours	36 Hours
95°F (35°C)	1 Hr	30 days	2 Hours	5 Hours	24 Hours

Color difference may occur between actual paint and color swatch on front of can.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS WARNING

Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants, and hat. May be fatal if swallowed or inhaled. Do not breathe vapor. While sanding boat surface, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute of Occupational Safety and Health. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

FIRST AID:

IF SWALLOWED:

- Call a poison control center or doctor immediately for treatment advice.
- Have person sip a glass of water if able to swallow.
- Do not induce vomiting unless told to do so by a poison control center or doctor.
- Do not give anything by mouth to an unconscious person.

IF ON SKIN OR CLOTHING:

- Take off contaminated clothing.
- Rinse skin immediately with plenty of water for 15-20 minutes.
- Call a poison control center or doctor for treatment advice.

IF INHALED:

- Move person to fresh air.
- If person is not breathing, call 911 or an ambulance, then give artificial respiration, preferably mouth-to-mouth if possible.
- Call a poison control center or doctor for further treatment advice.

IF IN EYES:

- Hold eye open and rinse slowly and gently with water for 15-20 minutes.
- Remove contact lenses, if present, after the first 5 minutes, then continue rinsing eye.
- Call a poison control center or doctor for treatment advice.

OTHER: Have the product container or label with you when calling a poison control center or doctor, or going for treatment.

ENVIRONMENTAL HAZARDS:

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill. Do not discharge effluent containing this product into lakes, streams, ponds, estuaries, oceans and other waters unless in accordance with the requirements of a National Pollution Discharge Elimination System (NPDES) permit and the permitting authority has been notified in writing prior to discharge. Do not discharge effluent to sewer system without previously notifying the local sewage treatment plant authority. For guidance contact your State Water Board or Regional Office of the EPA.

STORAGE AND DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are acutely hazardous. Improper disposal of excess pesticide, spray mixture or rinate is a violation of Federal Law. If these wastes cannot be disposed of by uses according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Non-refillable container. Do not re-use or refill this container. Triple rinse as follows: Empty the remaining contents into application equipment or a mix tank and drain for 10 seconds after the flow begins to drip. Fill the container 1/4 full with water and recap. Shake for 10 seconds. Pour rinate into application equipment or a mix tank or store rinate for later use or disposal. Drain for 10 seconds after the flow begins to drip. Repeat this procedure two more times.

For Chemical Emergency, Spill, Leak, Exposure or Accident, Call TollFree - Day or Night - **Chemtrec 1-800-424-9300.**

Medical Advisory Number - Contact your Local Poison Control Center or call **1-800-854-6813.**

YBE149/1

Interlux® are registered trademarks of Akzo Nobel.

Interlux®

International Paint LLC.
6001 Antoine Dr. Houston, TX USA 77091 • 713-682-1711



0 81948 00221 9

MADE IN THE U.S.A

yachtpaint.com

ZU0391 qa